



Product Information

ALL WAYS

Description

An entirely new concept in floor finishes. A detergent resistant acrylic polymer that dries to extreme hardness. It has beautiful luster with minimum of scuffing, and perfect leveling under all application conditions. The outstanding quality represented in this finish is the resistance to unsightly rubber marks.

WARNING: WET FLOORS ARE SLIPPERY. Use proper caution and display warning placards anytime floors are wet. This product is not recommended for exterior use or use on interior floors that are subject to standing water or wet conditions.

Recommended Uses

This product is recommended for finishing and maintaining asphalt tile, vinyl, vinyl composition, rubber, linoleum, seamless flooring, sealed wood, terrazzo, masonite and cork floors.

Directions

1. Thoroughly clean the floor and remove all old wax or finish using a solution of a concentrated wax and finish stripper. Pay particular attention to corners and baseboards to ensure that all old coatings have been removed.
2. Scrub rinse well with clear water, pick up with a wet vac or mop and allow to dry.
3. Apply the finish using a lamb's wool applicator, gravity flow applicator, or a rayon mop.
4. For optimum gloss and durability apply 3 or 4 coats. Be sure previous coat has been dry (tack free) at least 15 minutes before applying next coat.
5. Maintain by damp mopping with a neutral cleaner.
6. Recoat traffic lanes on an as required basis.
7. Spray buffing with a material designed for this type maintenance will restore gloss.
8. For best results, dust daily with a properly treated mop.

CAUTION: Contains polymer emulsions. Undiluted product may cause eye irritation. Avoid contact with eyes. Do not take internally.

FIRST AID: In case of contact, flush eyes with plenty of water for 15 minutes. If irritation persists, see a doctor.

KEEP OUT OF REACH OF CHILDREN KEEP FROM FREEZING FOR INDUSTRIAL & INSTITUTIONAL USE ONLY

Specifications

Type product	Metal crosslinked acrylic copolymer
Viscosity (Gardner-Holdt tube)	Less than A-1
Percent solids	16 ± 0.5
Flash point	None
Set to touch	20 minutes
Dry hard	40 - 50 minutes
Initial gloss (white vinyl, 60° meter)	76 - 78
Weight per gallon	8.58 lbs.
pH	8.45 ± 0.25
Leveling	Excellent
Freeze/thaw stability	Protect from freezing
Slip coefficient, James Machine O.T.A.T.	Over 0.5
Resistance to abrasion	Excellent
Resistance to black-marking	Excellent
Washability	Excellent
Coverage	1800 - 2000 sq. ft. per gallon
V.O.C.	355 gm/l