



# Product Information

## PERFECTION

### Description

Substantial changes in the methods of resilient tile floor maintenance require a new approach toward floor finish formulation.

The introduction of ultra high speed machines is one of these changes. The tremendous heat and friction generated by this equipment requires that the floor finish polymer react positively to the thermo-setting characteristics.

This product is an example of the new technology specifically formulated to be compatible with the new ultra high speed equipment.

### Recommended Uses

This floor finish is recommended for application on all types of resilient flooring such as vinyl composition, asphalt, vinyl, rubber and linoleum. It is also suitable for use on quarry tile, terrazzo and concrete. Do not use on glazed ceramic tile.

**WARNING: WET FLOORS ARE SLIPPERY.** Use proper caution and display warning placards anytime floors are wet. This product is not recommended for exterior use or use on interior floors that are subject to standing water or wet conditions.

### Directions

1. Thoroughly clean the floor and remove all old wax or finish using a solution of a concentrated wax and finish stripper. Pay particular attention to corners and baseboards to ensure that all old coatings have been removed.
2. Flood rinse well with clear water, pick up with a wet vac or mop and allow to dry.
3. Apply the finish using a rayon mop or gravity fed applicator.
4. Apply 2 or 3 more coats to obtain optimum gloss. Be sure previous coat has been dry (tack free) at least 15 minutes before applying next coat.
5. Maintain by damp mopping with a neutral cleaner.
6. Recoat traffic lanes on an as-required basis.
7. For high speed maintenance, burnish and use a high speed burnisher solution on an as-needed basis. A 1500 rpm machine is recommended with appropriate high speed pad.
8. For best results dust daily with a properly treated mop.

**CAUTION:** Contains polymer emulsions. Undiluted product may cause eye irritation. Avoid contact with eyes. Do not take internally.

**FIRST AID:** In case of contact, flush eyes with plenty of water for 15 minutes. If irritation persists, see a doctor.

**KEEP OUT OF REACH OF CHILDREN    KEEP FROM FREEZING    FOR INDUSTRIAL & INSTITUTIONAL USE ONLY**

### Specifications

Type product	Metal cross-linked acrylic
Clarity of dried film	Excellent
Viscosity (Gardner-Holdt tube)	Less than A-1
Percent solids	22 ± 0.5
Flash point	None
Set to touch	15 minutes
Dry hard	30 - 40 minutes
Resistance to cold water (48 hr. dry)	Excellent
Initial gloss (white vinyl, 60° meter)	85
Weight per gallon at 25° C	8.6 lbs.
pH	8.0 ± 0.5
Leveling	Excellent
Freeze/thaw stability	Passes 3 cycles
Resistance to abrasion	Excellent
Resistance to black-marking	Excellent
Washability	Excellent
Appearance	Opaque white
Coverage	1800 - 2000 sq. ft. per gallon
V.O.C.	175 gm/l